

62690 Ozokerite

Application:

Ozokerite wax is used in the manufacture of emulsions and crayons. It has very good properties as protective layer against water, water vapor, odor and oxygen.

Ozokerite melts at approx. 93 – 99°C and solidifies again at 86 – 80°C.
Ozokerite is soluble in aromatic solvents, e.g. Xylene, Toluol and Shellsol A.

Technical Data:

CAS No.:	8002-74-2
EINECS No.:	232-315-6
Solidification point:	80 - 86°C
Drop point:	93 - 99°C
Penetration (25°C):	ca. 17 dmm
Color:	white
Form:	prills