

98155 Starter Set Instacoll Gilding

Kölner Instacoll System

Instacoll Base and Activator

Highgloss gilding outdoors

Instacoll is a size for the attainment of a high gloss weather-resistant exterior and interior gilding. It can be used on nearly all substrates that have been prepared using standard accepted techniques to create weather-resistant surfaces. Do not use directly on glass outdoors. For indoor gilding it is sufficient to have or to prepare a non porous surface. Agate burnishing is not possible nor even necessary.

Before gilding *Instacoll* needs to be a completely dry film. This film will be activated with *Instacoll - Activator* prior to leaf application, preferably patent gold (transfer gold leaf). After activating the *Instacoll*-surface is now prepared that gold leaf adhere superbly with a maximum of burnish effect.

Application:

Porous surfaces such as row wood, stone, plaster... should first be coated with a 15% water/*Instacoll* diluted solution. After about 30 minutes of drying this coating can be covered with a more generous, full strength layer of *Instacoll*. As mentioned above some materials in weathering need more than a simple pre-paint with *Instacoll* to achieve a weather resistant coating. - The rules of the craft of painting have to be strictly observed!

- Apply *Instacoll* with a soft brush (nylon) or a sprayer. Dilute with water 5% to 10% if spraying.
- One or two evenly applied coats are sufficient. The last coat should be completely dry before applying the next layer.
- Wait at least 1 hour after the application the last *Instacoll* layer.
- Now you have about one hour "open time" to apply the gold leaf without using the Activator
- After the one hour "open time" you have to use the Activator. You can Activate again and again also after one day, two weeks, 6 months, also areas that has been activated can be activated again.

Activate

- Activate the dry and tackles surface of *Instacoll* with *Instacoll - Activator* using a cotton rag moistened with *Instacoll - Activator*. Rub the moistened rag across the *Instacoll* film up to a very thin and even size film results. This „film“ must be sparse that drying results in less than 2 minutes. Now you can apply gold leaf for another 50/60 minutes.
- Apply patent gold by pressing and rubbing a cotton ball on the back of transfer paper. Continues gilding require always activating the next plane. Overlapped activating onto a just laid leaf enables a seamless gilded surface.
Always let the Activator Size dry before applying the next leaf!
- After the entire surface is covered with metal, press again with the cotton ball the entire surface, especially the overlapping from the gold leaf. After this you can rub the surface with a cotton ball in one direction to get a high gloss gilding
- Faults can be filled using the above method or by applying *Instacoll - Activator* as described below. Also you can use very easily the instacoll clear to improve your result when you are not satisfied

Loose leaf may applied directly if the gold is laid on the **wet** *Instacoll-Activator*. Therefore the size should be brushed thinly but repeatedly. Similar to traditional water gilding, the leaf is immediately laid on the wet surface. After the surface has dried sufficiently, the leaf should be pressed again onto the surface with cotton. The resulting shine is not so brilliant as with „dry gilding“ mentioned before.